



weftron LOUVER_tron® 108

is a member within the **weftron.com** product group of High Performance Contact Systems.

Multiple consecutive copper contact plates, mounted on copper beryllium spring band, at a spacing of 3.32mm are offering precisely defined contact points in between mating conducting surfaces.

The separation of the contact spring function from the electrical conduction function gives **LOUVER_tron® 108** exceptionally high current carrying capacity. The number of contact plates applied, in conjunction with the associated metal components and the environment in which they are used, will precisely define the electrical performance characteristics of the complete system.

LOUVER_tron® 108 technical parameters are shown in the table on the backside of this data sheet. **weftron.com** offers a variety of application specific options, along with the associated machined metal components, in order to complete the final contact arrangement. Please consult us for any of your projects involving *connections with special requirements*.

weftron.com

fon: +49 (0)6232 602 946
priority@weftron.com

features

two component high performance contact band
separation of functions for electrical conduction and contact spring force
high conductive copper plates mounted on a strip of copper beryllium spring
dense arrangement of defined contact bridges at a 3.32mm spacing
various contact strip lengths for flat contacting arrangements
sliding and rotating contact feasibility
contact band width of 9.8mm

weftron LOUVER_tron[®] 108

Typ Type Type	Bandstärke Thickness Epaisseur mm	Streifenbreite Strip width largeur de bande mm	Kontakttraster contact spacing distance de contacts mm	Nennstrom Nominal Current Intensité nominale A	Kontaktkraft Contact force Force de contact N	Gleitkraft Sliding force Force d'insertion N	Part No. Teile Nr. Référence
LOUVER_tron [®] 108	0.20	9.8	3.32	60	8	3.5	Ltf-108-0.2-xx

xx = number of contact plates
xx= Anzahl Kontaktplatten
xx= nombre des contacts

All performance data refer to individual contact bridges and to silverplated copper contacts
Sämtliche Angaben gelten per Kontaktbrücke und für versilberte CU-Kontaktteile
Les performances indiquées s'entendent par pont et se réfèrent à des contacts en cuivre

Conversion factors for other material: Cu: 1
Reduktionsfaktoren für andere Metalle: E-AL: 0.75
Conversion pour d'autres matériaux: CuZn39PB3: 0.60

weftron.com

fon: +49 (0)6232 602 946
priority@weftron.com

Disclaimer:

"Although the information and recommendations set forth herein (hereinafter "Information") are presented in good faith and believed to be correct as of the date hereof, weftron gmbh makes no representations as to the completeness or accuracy thereof. Information and products supplied by weftron gmbh according to this information are supplied upon the condition that the persons receiving same will make their own determination as to their suitability for their purposes prior to use. In no event will weftron gmbh be responsible for damages of any nature whatsoever resulting from the use of any supplied products or resulting from the reliance upon information. weftron gmbh may change information on this data sheet without notification.